



Balanced Aramid Fabric

WOVEN FABRIC DATA SHEET

G. Angeloni reference

KK 300 T

CHARACTERISTICS	
Mass per unit area	gr/sqm.
Weave	
Standard Width	mm.
Laminate thickness	mm.
Other informations	

Nominal	Tolerance	Normative
305	± 5%	ISO 4605
2x2 Twill		ISO 2113
1200	± 2,5%	
0,52	± 15%	ISO 5084
Loomstate		

Nominal Construction	
Fibre description	
Thread Count	ends/cm.
Weight distribution	gr/sqm.
	%

WARP		WEFT	
HM Aramid Twaron 2200 3420 dtex		HM Aramid Twaron 2200 3420 dtex	
4,5	ISO 4602	4,5	ISO 4602
HM Aramid	153 50%	HM Aramid	153 50%

Note : Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

G. Angeloni srl

via Abate Tommaso , 72/A5 - 30020 Quarto d'Altino (VE) - ITALY

Tel. +39 0422 823801 - 780580 Fax +39 0422 782782

E-Mail : info@g-angeloni.com